

#### **ILACOLOR SP**

Simple yet good one-coat system available in many colours and metallic shades.

- 1. Good surface hardness
- 2. Good cleanability
- 3. Medium shine effect

## Properties

Number of layers	1
Coating thickness	12 - 20 μm / 0.47 - 0.79 mils
Curing temperature to approx	380 °C / 716 °F
Staining resistance	$\star$ $\star$ $\star$ $\star$

### Application

### Substrate

Application		Substrate	Pre-treatment	Suitability
Baking tins	$\checkmark$	aluminum	passivate free from chromium	<b>~~</b>
Grill- and roasting tins	$\checkmark$			
Semi-industrial baking applications	Not suitable	aluminized steel	passivate free from chromium	$\checkmark \checkmark \checkmark$
applications		carbon steel	phosphating	$\checkmark$

# **BAKEWARE SPRAY**



### **Cleaning and care instructions**

Wipe the outside of the tin with a wet cloth. If the baking, grill or casserole dish is stubbornly dirty, clean it under hot water, a mild washing-up liquid and the fine side of a dishwashing sponge or a soft dishwashing brush. We strongly advise against using cleaning metal sponges. Always wipe the mould dry before storing.

Coated items can be cleaned in the dishwasher, although this is not recommended due to the aggressive cleaning agents. Cleaning by hand is preferable.