

ILACOLOR R

Universal one or two-coat exterior system. Pure and brilliant colours are not possible due to the high curing temperature.

- PTFE-based exterior coating
- Very good stain resistance
- Good cleanability
- Best adhesion to the substrate
- Special colour effects only available as a twocoat system

Properties

Number of layers	1 - 2
Coating thickness	15 - 20 μm / 0.59 - 0.79 mils
Curing temperature to approx	420 °C / 788 °F
Service temperature Staining resistance	250 °C / 482 °F ★ ★ ★ ★ ★

Application



Substrate

Substrate	Pre-treatment	Suitability
pressed / forged alu	sandblasting with corundum	~ ~ ~
alu cast	sandblasting with corundum	~ ~ ~
stainless steel	sandblasting with corundum	√ √ √

COOKWARE (PTFE)



Cleaning and care instructions

Wipe the outside of the cookware with a wet cloth. For stubborn stains, clean the pan under hot water, a mild washing-up liquid and the fine side of a dishwashing sponge or a soft dishwashing brush. We strongly advise against using cleaning metal sponges. Always wipe the pan dry before storing it.

Coated pans can be cleaned in the dishwasher, although this is not recommended due to the aggressive cleaning agents. Cleaning by hand is preferable.